

Atlas

GENERAL INFORMATION

Composition	100% PES
Weight g/m ²	459g
Weight g/Lm	656g
Width	143cm
Min. usable Width	0cm
Piece Length	40m
Tariff code	54075300

CLEANING INSTRUCTIONS



TECHNICAL DATE

• MARTINDALE ABRASION ISO12947-2 1998	END POINT CHANGE IN COLOR	>45000 4/5 (6000 Cycles)		
• SEAM SLIPPAGE EN ISO 13936-2	WARP WEFT	3.33mm 3,33 mm		
• TEAR STRENGTH EN ISO 13937-3:2000	WARP WEFT	362,14N 101,12N		
• TENSILE STRENGTH ISO 13934-1	WARP WEFT	1830,61N 1643,43N	elongation elongation	40,12% 28,16%
• COLOUR FASTNESS EN ISO 105-X12	WARP DRY WARP WET WEFT DRY WEFT WET	4 4/5 4 4/5		
• COLOUR FASTNESS TO LIGHT EN ISO 105-B02	GRADE	Col 100: 5		
	GRADE	Col 101: 5		
	GRADE	Col 102: 5		
	GRADE	Col 200: 5		
	GRADE	Col 300: 6		
	GRADE	Col 400: 5		
	GRADE	Col 500: 3/4		
	GRADE	Col 501: 4		
	GRADE	Col 600: 5		
	GRADE	Col 601: 4/5		
	GRADE	Col 602: 4/5		
	GRADE	Col 700: 4/5		
	GRADE	Col 701: 4/5		
	GRADE	Col 702: 4/5		
	GRADE	Col 800: 3/4		
	GRADE	Col 801: 4		
	GRADE	Col 802: 5		
	GRADE	Col 803: 5/6		
	GRADE	Col 804: 5		
	GRADE	Col 900: 6		
	GRADE	Col 901: 6		

SYMPHONYMILLS

STOCK SUPPORTED FABRICS FROM BELGIUM

Technical sheet

- **PILLING ON MARTINDALE** **500 RUBS** 5
ISO 12945-2:2000 **1000 RUBS** 4/5
 2000 RUBS 4/5
 5000 RUBS 4/5
- **PILLING TEST** **GRADE** 4/5
BS5811-1986